

NYCOBASE PROPERTIES

PRODUCT NAME	Kinematic Viscosity at 40°C(mm ² /s)	Kinematic Viscosity at 100°C(mm ² /s)	Viscosity Index
MONOESTERS			
Nycobase8110	3.2	1.3	-
Nycobase9108	3.3	1.3	-
DIESTERS			
NycobaseADE	7.7	2.3	120
NycobaseSEH	12	3.2	153
NycobaseADD	14	3.6	145
NycobaseADT	26	5.3	136
NEOPOLYOL ESTERS			
Nycobase8210	8.4	2.5	140
Nycobase7300	14	3.4	120
Nycobase8317	17.5	4	130
Nycobase8103	19.6	4.4	136
Nycobase7450	20.2	4.4	128
Nycobase9300	21	4.6	140
Nycobase7400	22	4.7	134
Nycobase8311	22.6	4.9	148
Nycobase5750	24.5	5.1	140
Nycobase8410	29.1	5.8	147
Nycobase8318S	43	7.6	151
Nycobase3118	46	9.4	192
Nycobase20441	64	8.7	109
Nycobase1040X	94	10	88
NycobaseSTM	106	14.3	137
Nycobase9670X	174	17.3	107
Nycobase1060X	250	20	92
COMPLEX ESTERS			
Nycobase8355	152	20	152
Nycobase8828	223	28	164
Nycobase8361	316	32	142
Nycobase4045	424	43	153
Nycobase8397	1000	84	164
HX-1 CERTIFIED FOOD GRADE ESTERS			
Nycobase20307FG	11.7	3.3	164
Nycobase30401FG	20	4.4	136
Nycobase30409FG	21.2	4.6	141
Nycobase30502FG	23	4.9	148
Nycobase40810FG	45	8.1	157
Nycobase43203FG	330	33.2	142
Nycobase32506FG	390	25.3	89
SPECIALTY ESTERS			
Nycobase619	122	18	165
NycobaseADEP12	170	21	145
NycobaseLPG400	7000	450	228